



48 B Otis Street  
West Babylon, NY 11704  
Tel. 631-920-5079 Fax. 631-920-0503  
E-mail SalesSET@optonline.net  
www.SET-mfg.com

**Set-Cast 290**  
**Epoxy Casting Compound**  
**Room Temperature Cure**

**Set-Cast 290** is a 100% solids epoxy system. It is a filled, low cost, general purpose encapsulant. **Set-Cast 290** is designed for room temperature cure, and has excellent moisture resistance. It is also available as a fast cure system. **Set-Cast 290** is machine dispensable.

**PROPERTIES – UNCURED**

	<b>(Part A)</b>	<b>Part B</b>
Color, visual .....	Orange	Clear
Viscosity, ASTM-D-2393 (c.p.s. @ 25° C)...	7-10,000	5-700
Specific Gravity .....	3.63	0.96
Mixed Specific Gravity.....	2.77	
Mix Ratio (weight).....	100:3	
Mixed Viscosity, ASTM-D-2393 (@ 25° C)	5-8000	
Pot Life @ 25°C (100 grams) .....	40 minutes	

**PROPERTIES – CURED**

**PHYSICAL**

Hardness, ASTM-D-2240 (Durometer).....	Shore D 82
Tensile Strength, ASTM-D-638 .....	8,500 psi
Tensile Elongation, ASTM-D-638 .....	2 %
Flexural Strength, ASTM-D-790.....	9,500 psi
Coefficient of Thermal Expansion .....	20 x 10 <sup>-5</sup>
Heat Distortion Point.....	80°C
Water Absorption.....	0.08%
Dielectric Strength, ASTM-D-149 (volts/mil) .....	419
Dielectric Constant, ASTM-D-150 .....	3.5
Dissipation Factor, ASTM-D-150.....	0.035
Volume Resistivity, ASTM-D-257 (ohm-cm).....	1 x 10 <sup>14</sup>
Thermal Conductivity, BTU's.....	2

**MIXING INSTRUCTIONS**

Pre-mix Part A and Part B separately. Then measure 100:3 by weight (A to B). Mix thoroughly scraping the sides and bottom of the container. Evacuate and then pour into mold or cavity.

**CURE SCHEDULE**

Room temperature cure @75°F with full properties after 24 hours.  
To accelerate cure, allow 2 hours @ room temperature, then 2 hours @ 125°F.

**Read Warranty on Back of Technical Data Sheet.**

## **Warranty**

**Silicone & Epoxy Technology** accepts no liability, in negligence or otherwise, in this communication. Under no circumstances shall the company be liable for incidental, consequential or other damages from alleged negligence, breach of warranty, strict liability or any other theory, arising out of the use or handling of this product. The sole liability shall be the purchase price of the product. You should test the material to determine if the material is suitable, and/or claims are valid, in your particular circumstances. None of the possible or suggested uses of the materials in this communication are licensed under any Silicone & Epoxy Technology patent covering such use or a recommendation for use of such materials in the infringement of any patent.

### **Silicone & Epoxy Technology**

Phone: 631-920-5079      Fax: 631-920-0503

Place Orders To: [SalesSET@optonline.net](mailto:SalesSET@optonline.net)

[www.SET-mfg.com](http://www.SET-mfg.com)