

P.O. Box 363

High Point, NC 27261 Tel: 336-886-5018 Fax: 336-886-7122 www.silicones-inc.com

### RTV-2 Silicones Since 1974

# P-100

## **Product Information**

#### **General Information**

**P-100** is a low viscosity, medium tear strength, platinum-catalyzed, RTV-2 silicone rubber, which was designed to have outstanding heat and chemical resistance. It is easy to mix and de-air, and will cure with virtually no shrinkage. The speed at which the rubber hardens can be dramatically accelerated with heat or with **Pt Accelerator** at room temperature. **P-100** may show some inhibition sensitivity. **P-100** is extremely useful for casting solid polyurethane, polyurethane foam, polyesters, epoxies and some low melting point metals.

## **Typical Properties**

### **Uncatalyzed Compound**

ColorBase: Off-whiteActivator: BrownViscosity (cps)Base: 30,000-50,000Activator: 1,500-2,500Mixing Ratio (B/A)By weight: 100 / 10By volume: 100 / 13.2

**Viscosity** (cps) Mixed: 25,000-40,000

Working Time 1 to 2 hours
Cure Time 16-24 hours
Shelf Life 6 months

#### **Vulcanized (cured) Properties** (7 days @ 70° F / 50% relative humidity)

**Shore A Hardness** (±4) One day: 30 7 Days: 33

Tear Resistance (ASTM D624) $70 \pm 10 \text{ ppi}$ Tensile Strength (ASTM D412) $470 \pm 30 \text{ psi}$ Elongation (ASTM D412) $345 \pm 25 \%$ Service Temperature (° F)-60 to 625ShrinkagenilSpecific Gravity1.25

Specific Gravity

Coverage (in³ / lb)

Dielectric Strength (volts/mil)

Dielectric Constant (@ 100 HZ)

Dissipation Factor (@ 100 HZ)

Volume Resistivity (ohms/cm)

1.25

22.2

22.2

20.00

4.5 x 10<sup>14</sup>

The information contained in this data sheet is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee. Since the conditions of use are beyond our control, Silicones, Inc. disclaims any liability incurred in connection with the use of our products and information contained herein.